



BX2500 ARWS COPY PAPER A4



- ☐ **BASIS WEIGHT: 80 GSM (ISO 536)**
- ☐ **THICKNESS: 98 μ M (ISO 534)**
- ☐ **STIFFNESS MD: ≥ 75 MN (ISO 2493-1)**
- ☐ **STIFFNESS CD: ≥ 35 MN (ISO 2493-1)**
- ☐ **TENSILE MD: ≥ 4.4 KN/M (ISO 1924-2)**
- ☐ **BENDTSEN ROUGHNESS: 220 ML/MIN (ISO 8791-2)**
- ☐ **AIR PERMEABILITY: ≤ 1700 ML/MIN (ISO 5636-3)**
- ☐ **MOISTURE: 4.2% (ISO 287)**
- ☐ **FORMATION: ≥ 25 (INTERNAL METHOD)**
- ☐ **WHITENESS CIE: 146 (ISO 11475)**
- ☐ **BRIGHTNESS D65: 105% (ISO 2470-2)**
- ☐ **OPACITY: 93% (ISO 2471)**