

Einsatzempfehlung

Material	Stahl N/mm²				Rostfreie Stähle		Guss		NE-Metalle				Superleg.		Stahl gehärtet	
Zugfestigkeit	<500	<800	<1200 (<HRC38)	<1600 (<HRC48)	<800	<1200	GG	GGG	Al Knetleg.	Al SI<10%	Cu, Ms		Ti/Ni/Co <900	900-1500	HRC 48-57	HRC 58-63
41 14 328 040 - Vc (m/min)	16	14						10	20	16	16					
Kühlung	Emulsion	Emulsion						Emulsion	Emulsion	Emulsion	Emulsion					